

**AbiBow**ALTERNATIVE OFFSET is an uncoated mechanical paper designed for a variety of applications: book publishing, financial printing, annual reports, direct mail, inserts, healthcare directories and more. **AbiBow**ALTERNATIVE OFFSET provides excellent bulk and opacity at lighter weights. This paper uses 50% less wood fiber than uncoated freesheet in an equivalent basis weight.

**AbiBow**ALTERNATIVE BOOK offers the same great benefits in a smooth finish, made to caliper.

# AbiBowALTERNATIVE OPAQUE AbiBowALTERNATIVE OFFSET AbiBowALTERNATIVE BOOK

**AbiBow**ALTERNATIVE OPAQUE **Smooth Finish** ISO Brightness: 79  
*(NOTE: THIS GRADE IS NOT RUN TO CALIPER. IF YOU NEED A SPECIFIC CALIPER, PLEASE ORDER ALTERNATIVE BOOK)*

BASIS WT LBS 25x38x500	BASIS WT. GSM	TYPICAL CALIPER RANGE 1/1000"	OPACITY TAPPI
27	40	2.3—2.8	82
33	48.8	2.9—3.6	87.5

**AbiBow**ALTERNATIVE OFFSET **English Finish and Vellum Finish** ISO Brightness: 79  
*(NOTE: THIS GRADE IS NOT RUN TO CALIPER. IF YOU NEED A SPECIFIC CALIPER, PLEASE ORDER ALTERNATIVE BOOK)*

BASIS WT LBS 25x38x500	BASIS WT. GSM	TYPICAL CALIPER RANGE 1/1000"	OPACITY TAPPI
35	51.8	2.5—3.0 (EF), 3.0—3.6 (V)	88.5
40	59.2	2.7—3.3 (EF), 3.0—4.2 (V)	90
45	66.6	3.1—3.5 (EF), 3.3—5.3 (V)	92
50	74	4.2—5.8 (V)	93

**AbiBow**ALTERNATIVE BOOK (Blue White) ISO Brightness: 79  
*(RUN TO CALIPER)*

BASIS WT LBS 25x38x500	BASIS WT. GSM	CALIPER 1/1000"	PPI	OPACITY TAPPI
27	40	2.5*	800	82
30	44.4	2.5*	800	84
33	48.8	2.4—3.1	832-646	87.5
35	51.8	2.5—4.5	800-444	88.5
40	59.2	2.9—5.0	690-400	90
45	66.6	3.2—5.5	624-364	92
50	74	4.0—6.0	500-334	93

EF=English Finish \* Call for availability of additional calipers  
 V=Vellum  
**Note: All values represent targets.**  
**Products are subject to mill minimums. Please call to inquire.**  
**The AbitibiBowater housemark and logotype are registered trademarks of AbitibiBowater Incorporated.**

